

## GEOMETRICAL ISOMERISM IN Ru<sub>2</sub>Au HETEROMETAL ASSEMBLY: CIS-LINKING OF TETRACYANIDOAUARATE TO TETRAKIS( $\mu$ -BUTANOATO)DIRUTHENIUM

Masahiro Mikuriya<sup>ID a\*</sup>, Shun Kawauchi<sup>a</sup>, Ryoji Mitsuhashi<sup>ID b</sup>, Motohiro Tsuboi<sup>ID a</sup>,  
Makoto Handa<sup>ID c</sup>

<sup>a</sup>School of Biological and Environmental Sciences, Kwansei Gakuin University,  
1, Gakuen Uegahara, Sanda 669-1330, Japan

<sup>b</sup>Institute of Liberal Arts and Science, Kanazawa University, Kakuma 920-1192, Japan

<sup>c</sup>Department of Chemistry, Graduate School of Natural Science and Technology, Shimane University,  
1060 Nishikawatsu, Matsue 690-8504, Japan  
\*e-mail: junpei@kwansei.ac.jp

**Abstract.** A heterometal assembled complex of tetrakis( $\mu$ -butanoato)diruthenium(II,III) and tetracyanidoaurate(III) [Ru<sup>II</sup>Ru<sup>III</sup>(*n*-C<sub>3</sub>H<sub>7</sub>COO)<sub>4</sub>Au<sup>III</sup>(CN)<sub>4</sub>]<sub>n</sub> was synthesized and characterized by the elemental analysis and infrared spectroscopy. The single-crystal X-ray structure analysis revealed that the complex consists of zigzag chain molecules of alternating arrangement of the Ru<sub>2</sub>(*n*-C<sub>3</sub>H<sub>7</sub>COO)<sub>4</sub><sup>+</sup> and Au(CN)<sub>4</sub><sup>-</sup> units with *cis*-bridging mode of the Au(CN)<sub>4</sub><sup>-</sup> units. The temperature dependence of the magnetic susceptibility data (4.5—300 K) showed that the magnetic interaction between the dinuclear Ru<sup>II</sup>Ru<sup>III</sup> units (*S*=3/2) is negligibly small with a zero-field splitting parameter *D* value of 60 cm<sup>-1</sup>.

**Keywords:** dinuclear ruthenium carboxylate, tetracyanidoaurate, heterometal complex, X-ray crystallography, magnetic property.

Received: 23 February 2023/ Revised final: 31 March 2023/Accepted: 04 April 2023

---